



(11) **EP 2 147 075 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention of the grant of the patent:
05.12.2018 Bulletin 2018/49

(51) Int Cl.:
C04B 41/50 ^(2006.01) **C04B 41/00** ^(2006.01)
C04B 41/52 ^(2006.01) **C04B 41/65** ^(2006.01)
C04B 41/71 ^(2006.01) **C04B 111/82** ^(2006.01)

(21) Application number: **08754196.7**

(86) International application number:
PCT/US2008/005677

(22) Date of filing: **02.05.2008**

(87) International publication number:
WO 2008/140694 (20.11.2008 Gazette 2008/47)

(54) **WEAK ACID BASED CONCRETE STAIN**

AUF SCHWACHER SÄURE BASIERENDER BETONFARBSTOFF
TEINTURE POUR BÉTON À BASE D'ACIDE FAIBLE

(84) Designated Contracting States:
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MT NL NO PL PT RO SE SI SK TR

- **TAO, William**
Woodridge, Illinois 60517 (US)
- **NETHERTON, Jason, J.**
Kenosha, Wisconsin 53143 (US)
- **GEBHARD, Matthew, S.**
Carry, Illinois 60013 (US)

(30) Priority: **10.05.2007 US 746657**

(43) Date of publication of application:
27.01.2010 Bulletin 2010/04

(74) Representative: **Vossius & Partner**
Patentanwälte Rechtsanwälte mbB
Siebertstrasse 3
81675 München (DE)

(73) Proprietor: **SWIMC LLC**
Cleveland, Ohio 44115 (US)

(72) Inventors:

- **HERTZ, Sanford, Lee**
Hoffman Estates, Illinois 60192 (US)
- **DARASKEVICH, Ed**
Oswego, Illinois 60543 (US)

(56) References cited:
US-A1- 2004 151 950 US-A1- 2004 151 950
US-A1- 2006 023 042 US-A1- 2006 063 689
US-A1- 2006 063 689 US-A1- 2006 167 178

EP 2 147 075 B1

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

FIELD OF THE INVENTION

5 **[0001]** The present invention relates generally to compositions and methods which are adapted to impart color to cementitious or mineral substrate surfaces. Specifically, the present invention relates to a composition and method adapted to treat cementitious surfaces which have the advantage of using a non-corrosive acid-based solution.

BACKGROUND

10 **[0002]** Cement-based compositions enjoy broad application in construction materials, tile setting, wall and pool plasters, stucco, self leveling compounds, roofing tiles and cement patches. Concrete and like materials are produced from the alkaline earth metals typically by mixing portland cement with sand, gravel, and water. The reaction of the cement with the water produces among other things metal carbonates such as calcium carbonate. The calcium carbonate in the
15 mixture is insoluble in water but reacts readily with most acids.

[0003] There has been a desire for some time to produce colored concrete to improve the decorative appearance of concrete. For example, U.S. Pat. No. 3,930,740 discloses tools for imprinting non-repeating stone patterns in fresh concrete to which color is added. U.S. 5,735,094 discloses a process for applying an ornamental coating comprised of liquid mortar which includes a color pigment. The addition of dyes and pigments to the cementitious materials has also
20 enjoyed wide application in all of the above mentioned materials.

[0004] There are several processes for coloring or ornamenting a concrete surface that are known in the art. These include sweeping partially set concrete to produce a broom surface or adding a coloring agent that is mixed into the concrete blend. However, afterwards, a thorough clean-up of the applicator equipment is necessary, resulting in considerable labor and expense. This method is costly and inefficient, as coloring agents are expensive, become mixed
25 throughout the concrete, and are only needed at the surface where they are visible. More elaborate surface treatments are known, including embedding stones varying in size or color into concrete areas by means of cement or resin.

[0005] One of the more common processes known in the art for coloring or staining concrete involves washing a concrete surface with an acidic solution containing a metallic salt. After application of the acidic staining solution and development of the color, a neutralizing agent is commonly applied to the stained concrete and a clear protection
30 polymeric sealer coating is applied.

[0006] A second common method in the art of coloring concrete involves washing the concrete surface with an acidic solution to roughen or etch the surface; neutralize and rinse away the etching solution with a mixture of common baking soda and water; coloring the surface with a polymer based stain or paint; and finishing the surface with a clear coating.

[0007] Another known process involves washing a concrete surface with acidic solution to clean the concrete, applying a layer of polymers to the concrete surface, applying a first layer of an aqueous solution of cement and polymers to the coated concrete surface, applying a template with adhesive backing to selected regions of the first layer of cement and polymers, applying a second cement and polymer layer over the template and the first coating layer, applying colored materials to the second cement and polymer layer prior to the curing of the second layer, and removing the template to expose the colored concrete surface. A sealer may also be applied over the colored concrete surface.
35

[0008] However, these coating processes involve the use of highly corrosive acidic solutions, which are dangerous to handle. If the use of the acid is eliminated, the coloring of the concrete is not permanent and is prone to peeling and erosion. Consequently, there exists an unfulfilled need for a concrete coloring process that uses a permanent less corrosive coloring agent that results in a decorative, durable, coated concrete surface.
40

[0009] US 2006/0023042 A1 discloses liquid compositions for ink jet printing.

45 **[0010]** US 2006/0063689 A1 describes concrete cleaning and preparation compositions.

SUMMARY OF THE INVENTION

[0011] Traditional concrete acid stains, as described in US 2004/0151950 A1, use hydrochloric acid to decompose the calcium carbonate and calcium oxide in the concrete, and to facilitate the ion exchange with the metallic salt, which imparts the color to the surface of the material. However, the use of hydrochloric acid involves the production of excessive fumes of hydrogen chloride, which are irritating to the skin and eyes and toxic. In addition, the hydrochloric acid solution is very corrosive and thus dangerous to handle and use. The inventors have discovered that the use of an acid and a weak base, such as hydrochloric acid and urea, provides an effective and safe means to stain cementitious substrates.
50

[0012] Typically all acid stains must be rinsed after application to remove excessive salt precipitate. Acid stains that use hydrochloric acid must be neutralized prior to rinsing, or the runoff from the rinse can stain adjacent concrete. Typical neutralizing agents used are ammonia or sodium hydroxide, or baking soda solutions. An additional advantage of combining an acid with a weak base is that the stained concrete self neutralizes during the staining process. This
55

eliminates the need to go through a neutralization step before rinsing.

DETAILED DESCRIPTION OF THE INVENTION

5 **[0013]** The current invention relates to compositions and methods for imparting color to a cementitious or mineral substrate. The composition includes an acid with a pKa of less than 6, a weak base such that the conjugate acid of the weak base has a pKa of less than 7 and greater than the pKa of the acid, and one or more water soluble metallic salts, selected from the group consisting of chloride, sulfate, nitrate, nitrite, phosphate, and phosphonate salts of titanium, vanadium, chromium, manganese, iron, cobalt, nickel, copper, aluminum, magnesium, and barium.


10 **[0014]** In various embodiments, the water-soluble metal salts of the composition can include salts of the transition elements. In some embodiments, the weak base can decompose when it is applied to the cementitious materials such that the decomposition products are stronger bases.

[0015] The strength of a base is defined by the pKa of its conjugate acid. The higher the pKa of the bases conjugate acid the stronger the base. For example acetate is a weak base where the conjugate acid (acetic acid) has a pKa of 4.75. Lactate is a weak base where the conjugate acid (lactic acid) has a pKa of 3.86. Given this definition, acetate would be considered a stronger base than lactate.

15 **[0016]** Certain embodiments will include a weak base that can decompose into components that have a vapor pressure greater than 0.01psi at 25 °C upon application to substrate. In some embodiments, the acid is a hydrogen halide. In yet others, the weak base are preferably urea.

20 **[0017]** Weak bases useful in the present invention include:

(1) substituted ureas of the following formula



25 where R1, R2, R3 and R4 are C1-C10 carbon groups or hydrogen. For example urea, tetramethyl urea, acetylurea, imidazolidinone, or substituted imidazolidones, pyrimidinone, pyrimidinedione, and the like;

(2) amides such as formamide, and dimethyl formamide, or acetamides such as dimethyl acetamide, caprolactam; and, pyrrolidone;

30 (3) esters of carbonic acid such as alkyl and aryl carbonates, such as dimethyl carbonate, propylene carbonate, ethylene glycol bis methyl carbonate, ethyl M-tolyl carbonate;

(4) carbamates such as alkyl and aryl carbamates, such as ethyl ethylcarbamate, oxazolidinone, and oxazolidinedione; and,

35 (5) amino acids such as glycine, alanine, leucine, valine, phenylalanine, aspartic acid, glutamic acid, cysteine, lysine, and histidine.

[0018] Additional examples of weak bases include alkanolamines, including triethanolamine, diethanoamine, monoethanolamine and alkoxyated amines of the following formula $(HO-[(R)O]_x-R)_y-NH_{3-y}$, wherein the R is a C2 to C8 alkyl group, and x can vary from 1 to 100, and y can vary from can vary from 1 to 3; polymers with nitrogen-containing heterocyclic groups (including but not limited to pyridine, pyrimidine, imidazole, tetrazole, pyrazine, quinoline, isoquinoline, indole, isoindole, benzimidazole, purine, pyrrole, isopyrazole, quinazoline, pyridazine, pyrazine, cinnoline, phthalazine, quinoxaline, xanthine, hypoxanthine, and pteridine); polymers and copolymers of acrylamide, and cyclic amides such as caprolactam; pyrrolidone, polyvinyl pyrrolidone, copolymers of vinyl pyrrolidone, methacrylamide, polymethacrylamide, copolymers of methacrylamide, ammonia, guanidine, hydroxyurea, semicarbazide; mono-, di-, or tri(alkyl or aryl)urea, and wherein in the case of di(alkyl or aryl)urea the alkyl or aryl groups can be on the same or different nitrogen atoms, O-methyl hydroxyl amine (methoxylamine), aniline, and hydrazine. Preferred bases are nitrogenous bases. Preferred are substituted ureas. Most preferred is urea.

[0019] Acids useful in the present invention can include carboxylic acids such as acetic, maleic, citric, formic, and benzoic; phosphoric, phosphonic such as ethyl phosphonic acid; polyphosphoric acids such as pyrophosphoric, and hexameta phosphoric; sulfuric, sulfonic such as benzyl sulfonic acid, nitric or nitrous acid, hydrogen halides such as hydrogen fluoride, hydrogen chloride, hydrogen bromide, and hydrogen iodide. Preferred are phosphoric and polyphosphoric acids, nitric or nitrous acid, and hydrogen chloride. More preferred are phosphoric, pyrophosphoric, and hydrogen chloride. Most preferred is hydrogen chloride.

[0020] Metal salts in the various compositions of the invention include chloride, sulfate, nitrate, nitrite, phosphate, or phosphonate salts of titanium, vanadium, chromium, manganese, iron, cobalt, nickel, copper, aluminum, magnesium, or barium.

[0021] The compositions of the present invention can further comprise a metal ion complexing agent, such as EDTA, amino phosphonates sold under the trade name Dequest™, phosphate or polyphosphates. The compositions of the

present invention can further comprise a surfactant, dispersant, or organic solvent capable of improving the wetting of the composition.

[0022] Such solvents can include: water miscible solvents such as methanol, ethanol, propanol, acetone, ethylene glycol alkyl ethers, propylene glycol alkyl ethers and diacetone alcohol; and water immiscible solvents such as alkyl acetates, butyl acetate, methyl isoamyl ketone, amyl acetate, diisobutyl ketone, xylene, toluene, butanol, and mineral spirits. The compositions of the present invention can further comprise a defoamer such as a silicone, petroleum, mineral, natural oil, or a polymeric defoamer.

[0023] Typical surfactants can include anionic and nonionic surfactants. Suitable anionic surfactants include, for example, the higher fatty alcohol sulfates, such as sodium lauryl sulfate; alkylaryl sulfonates such as sodium or potassium isopropylbenzene sulfonates or isopropyl naphthalene sulfonates; alkali metal higher alkyl sulfosuccinates, such as sodium octyl sulfosuccinate, sodium N-methyl-N-palmitoylaurate, sodium oleyl isothionate; alkali metal salts and ammonium salts of alkylaryl polyethoxyethanol sulfates, sulfonates, or phosphates, such as sodium tert-octylphenoxypolyethoxyethyl sulfate having 1 to 50 oxyethylene units; alkali metal salts and ammonium salts of alkyl polyethoxyethanol sulfates, sulfonates, and phosphates; and alkali metal salts and ammonium salts of aryl polyethoxyethanol sulfates, sulfonates, and phosphates.

[0024] Suitable nonionic surfactants include alkylphenoxypolyethoxyethanols having alkyl groups of from about 7 to 18 carbon atoms and from about 6 to about 60 oxyethylene units, such as heptylphenoxypolyethoxyethanols, methyloctyl phenoxypolyethoxyethanols; polyethoxyethanol derivatives of methylene-linked alkyl phenols; sulfur-containing agents such as those made by condensing from about 6 to 60 moles of ethylene oxide with nonyl mercaptan, dodecyl mercaptan, or with alkylthiophenols wherein the alkyl groups contain from 6 to 16 carbon atoms; ethylene oxide derivatives of long chained carboxylic acids, such as lauric acid, myristic acid, palmitic acid, oleic acid, or mixtures of acids such as those found in tall oil containing from 6 to 60 oxyethylene units per molecule; analogous ethylene oxide condensates of long chained alcohols such as octyl, decyl, lauryl, or cetyl alcohols, ethylene oxide derivatives of etherified or esterified polyhydroxy compounds having a hydrophobic hydrocarbon chain, such as sorbitan monostearate containing from 6 to 60 oxyethylene units; block copolymers of ethylene oxide section combined with one or more hydrophobic propylene oxide sections.

[0025] Typical dispersants can include polymers and copolymers of ethylenically unsaturated carboxylic acids such as (meth)acrylic acid, fumaric acid, itaconic acid, maleic acid, maleic anhydride, and monoesters of fumaric acid; phosphorus acid monomers such as phosphoethyl (meth)acrylate and allyl phosphonic acid; and sulfur acid monomers such as 2-acrylamido-2-methyl-1-propanesulfonic acid, sulfoethyl (meth)acrylate, and vinyl sulfonic acid. This would include dispersants marketed under the trade name Tamol™. Citric acid, oxalic acid, phosphoric acid, pyrophosphoric acid, and poly phosphoric acids may also be employed.

[0026] The current invention also provides methods for staining the surface of a cementitious or mineral substrate comprising applying any of the compositions described herein to the surface of a cementitious or mineral substrate. The methods can be done in a single operation comprising:

- (a) completely wetting the surface with an excess of the stain solution
- (b) permitting the composition to react with the substrate and develop color,
- (c) permitting said stain pigment to dry in place
- (d) optionally applying an acid neutralizing solution to the stained cementitious or mineral surface

[0027] Neutralizing solutions can include aqueous solutions of weak bases such as carbonate and bicarbonate salts such as sodium, potassium, lithium, cesium, ammonium (bi)carbonate; or phosphate salts such disodium, dipotassium, dilithium, dicesium, or diammonium phosphate; or organic alkalinity sources such as alkylamines and alkanolamines.

[0028] A method of the current invention for staining the surface of a cementitious or mineral substrate is also provided wherein a transparent wax or polymeric coating is applied to the previously stained concrete or mineral substrate.

[0029] Under certain circumstances it may be desirable to apply a wax clear coating to the previously stained concrete. Typical waxes useful in the present invention include: natural plant or beeswaxes, paraffin, carnauba, and these aforementioned natural waxes modified with organic polymers such as polyethylene, polypropylene, or polytetrafluoroethylene.

[0030] Typical polymers useful in the present invention include: acrylic, styrene-acrylic, polyurethane, polyester, alkyd, epoxy-ester, silicone, and epoxy-amide. It is particularly advantageous to utilize polymer chemistries which crosslink after application over the stained concrete. Examples of suitable crosslinking polymers would be those employing air curable drying oil functionality, epoxy-amide reactions, siloxane condensation, hydrazide-carbonyl reactions, aziridine-acid reactions, isocyanate-hydroxy reactions, or carbodiimide-acid reactions. Preferred are those chemistries which offer a high degree of wear resistance. Most preferred are air drying epoxy-esters, two component epoxy amides, air curable alkyds, and aziridine crosslinked polyurethanes.

[0031] The stain can be applied by any conventional means known to those skilled in the art, for example by spraying or brushing it onto the concrete surface. Typically, the method of application will affect the final outcome. For example,

EP 2 147 075 B1

spraying on the stain will create a more natural look, while brushing will create a more uniform outcome. The use of multiple coats involving different stains will create a greater variety of successful color choices.

EXAMPLES

[0032] The following are non-limiting examples of stain compositions which serve to further illustrate advantages of the disclosed invention.

Example 1

[0033]

| Material | Weight (lb) | Vol (gal.) |
|--------------------------------|-------------|------------|
| Water | 54.75 | 6.57 |
| Urea monohydrochloride | 9 | 0.89 |
| 32% FeCl ₂ solution | 37.5 | 3.51 |
| Silicone defoamer | 0.1 | 0.011 |
| Total | 101.35 | 10.98 |

¹ Proprietary commercially available foam destroying polymers and polysiloxanes This example provides for a "fawn" or tan colored stain material.

Example 2

[0034]

| Material | Weight (lb) | Vol (gal.) |
|--------------------------------------|-------------|------------|
| Water | 48.26 | 5.79 |
| Urea monohydrochloride | 9 | 0.89 |
| CuCl ₂ ·2H ₂ O | 15.3 | 0.72 |
| Water | 18 | 2.16 |
| 32% FeCl ₂ solution | 9 | 0.84 |
| Silicone defoamer ¹ | 0.1 | 0.012 |
| Total | 99.66 | 10.41 |

¹ Proprietary commercially available foam destroying polymers and polysiloxanes This example provides for an olive-colored or green stain material.

Example 3

[0035]


| Material | Weight (lb) | Vol (gal.) |
|--------------------------------------|-------------|------------|
| Water | 19.89 | 2.38 |
| Urea monohydrochloride | 9.89 | 0.98 |
| Silicone defoamer ¹ | 0.1 | 0.011 |
| FeCl ₃ Solution, 40% | 31.25 | 2.67 |
| MnCl ₂ ·4H ₂ O | 21.43 | 1.27 |
| Urea monohydrochloride | 1.75 | 0.17 |
| Water | 15.78 | 1.89 |
| Total | 100.09 | 9.37 |

¹ Proprietary commercially available foam destroying polymers and polysiloxanes

[0036] This example provides for a "coffee" or brownish colored stain material. These embodiments or examples should be considered to be non-limiting and are presented to illustrate just a few of the possibilities of the compositions and methods of the present invention. While the principles of this invention have been described in connection with specific embodiments, it should be clearly understood that these descriptions are made only by way of example and are not intended to limit the scope of the invention. As such, the present invention may be embodied in other specific forms without departing from the spirit or essential attributes thereof, and, accordingly, reference should be made to the appended claims, rather than to the foregoing specification as indicating the scope of the invention.

Claims

1. A composition for imparting color to a cementitious or mineral substrate, the composition comprising:
 - a. an acid which has a pKa less than 6;
 - b. a weak base, wherein the conjugate acid of the weak base has a pKa less than 7 and greater than the pKa of the acid;
 - c. one or more water soluble metallic salts selected from the group consisting of chloride, sulfate, nitrate, nitrite, phosphate, and phosphonate salts of titanium, vanadium, chromium, manganese, iron, cobalt, nickel, copper, aluminum, magnesium, and barium, capable of imparting a color when applied to the cementitious or mineral substrate.
2. The composition of claim 1, wherein the acid has a pKa less than 5.
3. The composition of claim 1, wherein the acid has a pKa less than 1.
4. The composition of claim 1, wherein the weak base can decompose upon application to cementitious materials into components that are stronger bases.
5. The composition of claim 1, wherein the weak base can decompose upon application to cementitious materials into components that have a vapor pressure greater than 69 Pa (0.01psi) at 25 °C.
6. The composition of claim 1, further comprising a metal ion complexing agent.
7. The composition of claim 1, further comprising a surfactant, dispersant, or organic solvent capable of improving the wetting of the composition.
8. The composition of claim 1, further comprising a silicone, petroleum, mineral, natural oil, or polymeric defoamer.
9. A method for staining the surface of a cementitious or mineral substrate comprising applying the composition of claim 1 to the surface of a cementitious or mineral substrate.
10. The method for staining the surface of a cementitious or mineral substrate according to claim 9, the method in a single operation comprising:
 - (a) completely wetting the surface with an excess of the composition of claim 1;
 - (b) permitting the composition to react with the substrate and develop color;
 - (c) permitting said composition to dry in place;
 - (d) optionally applying an acid neutralizing solution to the stained cementitious or mineral surface.
11. The method for staining the surface of a cementitious or mineral substrate according to claim 9, further comprising the application of a transparent polymeric coating or of a wax coating to the stained concrete or mineral substrate.
12. The composition of claim 1 or the method according to claim 9, wherein the weak base is selected from ureas of the formula




wherein R₁, R₂, R₃ and R₄ are C1-C10 carbon groups or hydrogen, and/or

wherein the acid that has a pKa less than 6 is selected from the group consisting of phosphoric and polyphosphoric acids, nitric and nitrous acid, and hydrochloric acid.

5 **Patentansprüche**

1. Eine einem zementartigen oder mineralischen Substrat Farbe verleihende Zusammensetzung, wobei die Zusammensetzung umfasst:
 - 10 a. eine Säure, welche einen pKa-Wert von weniger als 6 aufweist;
 - b. eine schwache Base, wobei die konjugierte Säure der schwachen Base einen pKa-Wert von weniger als 7 und größer als der pKa-Wert der Säure aufweist;
 - 15 c. ein oder mehrere wasserlösliche Metallsalze, ausgewählt aus der Gruppe bestehend aus Chlorid-, Sulfat-, Nitrat-, Nitrit-, Phosphat- und Phosphonatsalzen von Titan, Vanadium, Chrom, Mangan, Eisen, Kobalt, Nickel, Kupfer, Aluminium, Magnesium und Barium, die, wenn auf das zementartige oder mineralische Substrat aufgetragen, eine Farbe verleihen können.
2. Die Zusammensetzung gemäß Anspruch 1, wobei die Säure einen pKa-Wert von weniger als 5 aufweist.
- 20 3. Die Zusammensetzung gemäß Anspruch 1, wobei die Säure einen pKa-Wert von weniger als 1 aufweist.
4. Die Zusammensetzung gemäß Anspruch 1, wobei die schwache Base sich beim Auftragen auf zementartige Materialien in Komponenten zersetzen kann, die stärkere Basen sind.
- 25 5. Die Zusammensetzung gemäß Anspruch 1, wobei die schwache Base sich beim Auftragen auf zementartige Materialien in Komponenten zersetzen kann, welche einen Dampfdruck von mehr als 69 Pa (0,01 psi) bei 25°C aufweisen.
6. Die Zusammensetzung gemäß Anspruch 1, weiter umfassend ein Metallionenkomplexierungsmittel.
- 30 7. Die Zusammensetzung gemäß Anspruch 1, weiter umfassend ein grenzflächenaktives Mittel, Dispergiermittel oder organisches Lösungsmittel, welches in der Lage ist, die Benetzung der Zusammensetzung zu verbessern.
8. Die Zusammensetzung gemäß Anspruch 1, weiter umfassend einen Silikon, Erdöl, Mineralien, natürliches Öl oder Polymer enthaltenden Entschäumer.
- 35 9. Ein Verfahren zur Färbung der Oberfläche eines zementartigen oder mineralischen Substrats, umfassend das Auftragen der Zusammensetzung gemäß Anspruch 1 auf die Oberfläche eines zementartigen oder mineralischen Substrats.
- 40 10. Das Verfahren zur Färbung der Oberfläche eines zementartigen oder mineralischen Substrats gemäß Anspruch 9, wobei das Verfahren in einem einzigen Arbeitsgang umfasst:
 - 45 (a) vollständiges Benetzen der Oberfläche mit einem Überschuss der Zusammensetzung gemäß Anspruch 1;
 - (b) Reagieren lassen der Zusammensetzung mit dem Substrat und Entwickeln lassen von Farbe;
 - (c) Trocknen lassen der Zusammensetzung an Ort und Stelle;
 - (d) gegebenenfalls Auftragen einer säureneutralisierenden Lösung auf die eingefärbte zementartige oder mineralische Oberfläche.
- 50 11. Das Verfahren zur Färbung der Oberfläche eines zementartigen oder mineralischen Substrats gemäß Anspruch 9, weiter umfassend das Auftragen einer transparenten polymeren Beschichtung oder einer Wachsbeschichtung auf das gefärbte Beton- oder mineralische Substrat.
- 55 12. Die Zusammensetzung gemäß Anspruch 1 oder das Verfahren gemäß Anspruch 9, wobei die schwache Base ausgewählt ist aus Harnstoffen der Formel



wobei R_1 , R_2 , R_3 und R_4 C1-C10-Kohlenstoffgruppen oder Wasserstoff sind, und/oder wobei die Säure, welche einen pKa-Wert von weniger als 6 aufweist, ausgewählt ist aus der Gruppe bestehend aus Phosphor- und Polyphosphorsäuren, Salpetersäure und salpetriger Säure und Salzsäure.

5

Revendications

10

1. Composition pour communiquer de la couleur à un substrat cimentaire ou minéral, la composition comprenant :

15

- a. un acide qui présente un pKa inférieur à 6 ;
- b. une base faible, dans laquelle l'acide conjugué de la base faible présente un pKa inférieur à 7 et supérieur au pKa de l'acide ;
- c. un ou plusieurs sels métalliques solubles dans l'eau choisis dans le groupe consistant en chlorure, sulfate, nitrate, nitrite, phosphate, et des sels de phosphanate de titane, vanadium, chrome, manganèse, fer, cobalt, nickel, cuivre, aluminium, magnésium, et baryum, capables de communiquer une couleur lorsqu'ils sont appliqués au substrat cimentaire ou minéral.

2. Composition selon la revendication 1, dans laquelle l'acide présente un pKa inférieur à 5.

20

3. Composition selon la revendication 1, dans laquelle l'acide présente un pKa inférieur à 1.

4. Composition selon la revendication 1, dans laquelle la base faible peut se décomposer par application à des matériaux cimentaires en des constituants qui sont des bases plus fortes.

25

5. Composition selon la revendication 1, dans laquelle la base faible peut se décomposer par application à des matériaux cimentaires en des constituants qui présentent une pression de vapeur supérieure à 69 Pa (0,01 psi) à 25°C.

6. Composition selon la revendication 1, comprenant de plus un agent complexant un ion de métal.

30

7. Composition selon la revendication 1, comprenant de plus un tensioactif, dispersant ou solvant organique capable d'améliorer le mouillage de la composition

8. Composition selon la revendication 1, comprenant de plus un antimousse contenant du silicone, du pétrole, un minéral, une huile naturelle, ou un antimousse polymère.

35

9. Procédé pour colorer la surface d'un substrat de ciment ou minéral comprenant l'application de la composition selon la revendication 1 à la surface d'un substrat cimentaire ou minéral.

40

10. Procédé pour colorer la surface d'un substrat cimentaire ou minéral selon la revendication 9, le procédé dans une opération unique comprenant :


- (a) le mouillage complet de la surface avec un excès de la composition selon la revendication 1;
- (b) le laisser la composition réagir avec le substrat et développer de la couleur ;
- (c) le laisser ladite composition sécher sur place ;
- (d) éventuellement l'application d'une solution neutralisant l'acide à la surface cimentaire ou minéral colorée.

45

11. Procédé pour colorer la surface d'un substrat cimentaire ou minéral selon la revendication 9, comprenant de plus l'application d'un revêtement polymère transparent ou d'un revêtement de cire au substrat cimentaire ou minéral coloré.

50

12. Composition selon la revendication 1 ou procédé selon la revendication 9, dans laquelle la base faible est choisie parmi des urées de la formule



55

dans laquelle R_1 , R_2 , R_3 et R_4 sont des groupes carbonés en C1-C10 ou un atome d'hydrogène, et/ou dans laquelle l'acide qui présente un pKa inférieur à 6 est choisi dans le groupe consistant en acides phosphorique et polyphosphorique, acides nitrique et nitreux, et acide chlorhydrique.

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 3930740 A [0003]
- US 5735094 A [0003]
- US 20060023042 A1 [0009]
- US 20060063689 A1 [0010]
- US 20040151950 A1 [0011]